

# HYPERDESMO®-ADY-E WHITE

## One-component, semi-glossy, aliphatic, elastic polyurethane Top Coat.

### DESCRIPTION

**HYPERDESMO®-ADY-E WHITE** is a one-component polyurethane coating, that contains specialty inorganic fillers that offer superior hiding power. This allows minimal consumption of material and also omitting of a second coat (in cases of simple UV protection not traffic resistance) resulting in overall cost reduction. The material is based on the very successful product HYPERDESMO-ADY-E so it has similar elastomeric properties with HYPERDESMO products. It is based on pure elastomeric hydrophobic polyurethane resin, which results in excellent mechanical, chemical, thermal, UV and natural element resistance properties.

Apply with brush, roller or airless spraying in one or two coats. Minimum consumption per coat: 0.250 kg/m<sup>2</sup>.

### RECOMMENDED FOR

- Top-coating **HYPERDESMO®** range of products.
- Top-coating flooring applications

### LIMITATIONS

Not recommended for:

- Unsound substrates,
- application in thick coats.

### FEATURES & BENEFITS

- Excellent hiding power even in one coat
- Traffic resistant
- Strong and uniform adhesion on almost any type of surface,
- highly hydrophobic,
- highly durable when exposed to the natural elements, maintains its elasticity even down to

-40 °C,

- excellent heat and ultraviolet/UV resistance, it will not yellow, peel or soften up to 80 °C,
- outstanding resistance to chemicals and mechanical stresses (high tensile strength and abrasion resistance),

### APPLICATION PROCEDURE

Clean the surface using a high pressure washer, if possible. Remove oil, grease and wax contaminants. Cement laitance, loose particles, mould release agents, cured membranes, etc. must be removed. Further primer information available on request. The application surface must be **dry**.

### Preparation:

When stirring, take care not to introduce air in the fluid, which may result in bubbling on the cured membrane. Stirring can either be done manually or with a with a low speed (300 rpm) mixer. A small sediment may form in the pail after prolonged storage. This can be homogenized in the product with mechanical mixing.

### Application:

Apply with brush, roller or airless spraying in one or two coats. Do not exceed 48 hours between coats.

### CONSUMPTION

0.3-0.5 kg/m<sup>2</sup> in one or two coats.

### CLEANING

Clean tools and equipment first with paper towels

## HYPERDESMO<sup>®</sup>-ADY-E WHITE

and then using SOLVENT-01. Rollers will not be re-usable.

### PACKAGING

5 Kg, 20 Kg

### SHELF LIFE

Can be kept for 12 months minimum in the original unopened pails in dry places and at temperatures of 5-25 °C. Once opened, use as soon as possible.

### SAFETY INFORMATION

Contains volatile flammable solvents. Apply in well-ventilated, no smoking areas, away from naked flames. In closed spaces use ventilators and carbon active masks. Keep in mind that solvents are heavier than air so they creep on the floor. The MSDS (Material Safety Data Sheet) is available on request.

### TECHNICAL SPECIFICATIONS

#### In liquid form (before application):


PROPERTY	UNITS	METHOD	SPECIFICATION
Viscosity (Brookfield)	cP	ASTM D2196-86, @ 25 °C	400-600
Specific weight	gr/cm <sup>3</sup>	ASTM D1475 / DIN 53217 / ISO 2811, @ 20 °C	1.2
Tack free time, @ 77 °F (25 °C) & 55% RH	hours	-	6-8
Recoat time	hours	-	24

#### The cured membrane:

PROPERTY	UNITS	METHOD	SPECIFICATION
Service temperature	°C	-	-40 to 80
Max. temperature short time (shock)	°C	-	200
Hardness	Shore D	ASTM D2240 / DIN 53505 / ISO R868	40
Tensile strength at break @ 23 °C	Kg/cm <sup>2</sup> (N/mm <sup>2</sup> )	ASTM D412 / EN-ISO-527-3	40
Percent elongation @ 23 °C	%	ASTM D412 / EN-ISO-527-3	> 300
Water vapor transmission	gr/m <sup>2</sup> .hr	ASTM E96 (Water Method)	0.8
Thermal resistance (100 days @ 80 °C)	-	EOTA TR011	passed

## HYPERDESMO®-ADY-E WHITE

QUV Accelerated Weathering Test (4hr UV, @ 60 °C (UVB-Lamps) & 4hr COND @ 50 °C)	-	ASTM G53	passed (2000 hours)
Hydrolysis (Potassium Hydroxide 8%, 10 days @ 50 °C)	-	-	no significant elastomeric property change
Hydrolysis (Sodium Hypochlorite 5%, 10 days)	-	-	no significant elastomeric property change
Water absorption	-	-	< 1.4%



### ELONGATION CHART: CHEMICAL & HYDROLYTIC RESISTANCE

## HYPERDESMO<sup>®</sup>-ADY-E WHITE

- HYPERDESMO<sup>®</sup>-ADY-E, fully cured
- Hydrolysis (HCl, PH=2, 2 weeks, RT)
- Hydrolysis (KOH, 8%, 15 days @ 50°C)
- QUV (1000 hrs).

---

NONE OF OUR PUBLISHED INSTRUCTIONS AND SPECIFICATIONS, IN WRITING OR OTHERWISE, ARE BINDING EITHER IN GENERAL OR WITH RESPECT TO ANY THIRD PARTY RIGHTS, OR DO THEY RELIEVE INTERESTED PARTIES OF THEIR DUTY TO SUBJECT THE PRODUCT TO AN ADEQUATE EXAMINATION OF ITS SUITABILITY. IN NO EVENT WILL ALCHIMICA S.A. BE RESPONSIBLE FOR DAMAGES OF ANY NATURE, WHATSOEVER, RESULTING FROM THE USE OF OR RELIANCE UPON INFORMATION OR THE PRODUCT TO WHICH INFORMATION REFERS.

---

