



ACETOXY SILICONE BATHROOMS AND KITCHENS

DATA SHEET
12/2020



DESCRIPTION:

One part, acetic acid curing, silicone rubber based sealant. Contains a fungicide anti-mildew agent.

PROPERTIES:

Single -component system easy to apply. Reticulates at environmental temperature. When in contact with atmospheric humidity, it becomes a rubber with excellent technical properties and with a high resistance the inclemency of the weather.

APPLICATIONS:

- Sealing joints between glass and frameworks and joints between frameworks.
- Sealing of shower partitions.
- When, in general, a joint is subjected to high humidity with moderate temperatures.
- DIY (cars, boats, caravanes, etc...)

Due to its acid reticulation, **BATHROOMS AND KITCHENS** should not be applied on the following substrates:

- Construction materials such as concrete, masonry (and similar)
- Ferrous metals, copper and brass.
- Rubber, since the sealant may discolour.

For those cases, QUILOSA markets a wide range of non-acid sealants.

BATHROOMS AND KITCHENS should not be used for aquariums.

10 YEAR WARRANTY: Does not discolor due to mold growth. Quilosa Baths and Kitchens is guaranteed to stop mold growth for 10 years. Our guarantee consists in the replacement of the necessary product to make the seal. * **WARNING:** Quilosa bathrooms and kitchens are not a substitute for the regular cleaning necessary to eliminate excess soap and moisture that causes mold growth.

CERTIFICATIONS:

CE Mark: EN 15651-2 G-CC / EN15651-3 S Dop n°:SIB0000103 <http://ce.selena.com/>

TECHNICAL FEATURES:

UNCURED BATHROOMS AND KITCHENS			CURED BATHROOMS AND KITCHENS (4 weeks at 23°C and 55% H.R.)		
Appearance:	Pasta cremosa homogénea.		Appearance:	Similar to rubber	
Slump resistance (ISO 7390):	mm	0	Shore A hardness (ISO 868):	17±2	
Tack free (ASTM C-679-71):	Minutes	10-15	Elastic recovery (ISO 7389):	%	98
Skin over time (BS 5889 Ap.A):	Minutes	20-30	Modulus 100% (ISO 37):	MPa	0,33-0,36
Curing rate at 23°C And 55% h.r.:	mm/day	3-4	Tensile strength (ISO 37):	MPa	1,30-1,50
Application Temperature:	°C	+5 to +50	Elongation at break (ISO 37):	%	450-550
			Joint Movement	%	25
			Temperature range in service:	°C	-50 to +150



Quilosa - Selena Iberia S.L.U.
Centro empresarial Rivas Futura, C/ Marie Curie 19, Planta 6.1, 28521 Rivas, Madrid, Spain,
Tel: +34 902 02 18 02 – Fax: +34 914 999 796, info@quilosa.es, www.quilosa.com



ACETOXY SILICONE BATHROOMS AND KITCHENS

DATA SHEET
12/2020

CHEMICAL RESISTANCE:

Water , soapy water, brine:	Excellent.
Inorganic diluted acids and alkalis:	Very good.
Mineral oils and grease:	Very good.
Oil, fuel, hydrocarbons:	Very good.
Other products:	Consult.

INSTRUCTIONS:

Treatment of the surfaces:

The surfaces must be clean and dry. If necessary, in addition to mechanical means, cleaning with non-grease solvent such as acetone is recommended. For joints that are to be subjected to major stress, we suggest the use of a primer, appropriate for each type of substrate:

PRIMER C-27: For porous materials and general construction use.

(See technical data)

With glass and enamels, better results are obtained without primer.

Any material not known to the user in terms of adhesiveness must first be tested by or consulted with our technical department.

Procedure:

Cut off cap from adapter nipple, screw the nozzle on the cartridge, clip the tip of the nozzle to required opening and insert into caulking gun. Fill in the appropriately treated joint with **BATHROOMS AND KITCHENS**. In order to avoid messing the edges, they may be protected with masking tape. For a better finish, the seal may be smoothed with a spatula.

Yield:

The following formula is an approximate guideline in order to calculate foreseen yield for a standard cartridge of **BATHROOMS AND KITCHENS**:

$$L = \frac{280}{A \times D}$$

Where:

L = Length of sealant in metres obtained per cartridge of **BATHROOMS AND KITCHENS**.

A= Width of the joint in mm.

D= Depth of the joint in mm.

Further treatment

BATHROOMS AND KITCHENS may not be painted or varnished.

STORAGE:

Keep in a cool, dry place.

Lifetime: cartridges 24 months, tubes 36 months.

PRESENTATION:

In 100 cc. Plastic tubes.

In 280 cc. Plastic cartridges

COLOURS:

Translucent

White

CLEANING:

Fresh product is easily removed with an organic solvent. When cured it can be removed by mechanical mean only



ACETOXY SILICONE BATHROOMS AND KITCHENS

DATA SHEET
12/2020

HEALTH & SAFETY:

While curing **BATHROOMS AND KITCHENS** splits off acetic acid, therefore, the working area should be well ventilated.

Due to possible irritation, all contact of the product with eyes or mucous areas must be avoided. If contact occur, rinse the affected area thoroughly with plenty of water and, if necessary, see a doctor. The rubber obtained after curing can be handled without risk.

Primers used with **BATHROOMS AND KITCHENS** contain solvents flammable at air temperature. Do not smoke or use unprotected flame near the working area. If eyes are splashed, rinse thoroughly with plenty of water, otherwise, see a doctor.

Use gloves, and in case of splashing, wash with industrial detergent when the product is still fresh.
DO NOT WASH HANDS WITH SOLVENTS.

For more information, request Safety Data Sheet.

"The information contained herein is offered in good faith based on Selena's research and is believed to be accurate. However, because conditions and methods of use of our products are beyond our control, this information shall not be used in substitution for customer's tests to ensure that Selena's products are fully satisfactory for your specific applications. Selena's sole warranty is that the product will meet its current sales specifications. Your exclusive remedy for breach of such warranty is limited to refund of purchase price or replacement of any product shown to be other than as warranted. Selena FM S.A. specifically disclaims any other expressed or implied warranty of fitness for a particular purpose or merchantability. Selena disclaims liability for any incidental or consequential damages. Suggestions of use shall not be taken as inducements to infringe any patent.

Technical indications and data appearing in this brochure are based on our current knowledge and experience and we decline all responsibility for consequences derived from inadequate use. Therefore, our guarantee is limited exclusively to the quality of the product supplied. This technical information can be modified without notice. If necessary request it periodically."



Quilosa - Selena Iberia S.L.U.

Centro empresarial Rivas Futura, C/ Marie Curie 19, Planta 6.1, 28521 Rivas, Madrid, Spain,
Tel: +34 902 02 18 02 – Fax: +34 914 999 796, info@quilosa.es, www.quilosa.com