

TESSAROL varnish for boats

AREA OF APPLICATION

For lacquering wood indoors and outdoors: doors, wooden paneling, cork, garden furniture, boats...

PROPERTIES

- resistant to high humidity and large temperature differences
- good levelling
- stable gloss
- easy application
- resistant to household cleaning agents

TECHNICAL DATA

COMPOSITION	modified alkyd binder, solvent
COLOR SHADES	colourless
TINTING	
GLOSS	glossy
DENSITY	0,9 g/ml
THINNING	TESSAROL thinner, max. 5 %
EU VOC category and limits	IIA(e), 400 g/l (2010); the product contains: max. 400 g/l
PACKAGING UNITS	0,2 I, 0,75 I, 2,5 I
SHELF LIFE	The shelf life of an originally sealed and suitably stored product (temperature ranging from +5 C to
	+35 C in a dry place) is indicated on the packaging

INSTRUCTIONS FOR USE

thinning	viscosity (DIN 4 mm)	nozzle	pressure	
if necessary - max.5%				
max. 5%	approx. 40 sec.	1,2 – 1,5 mm	3 – 4 bar	
	delivery	0,23 - 0,28 mm	120 - 160 bar	
The paint, air and surface temperature should be at least +5 °C.				
Dust dry in approx. 3 hours, touch dry in 4 - 5 hours, recoatable after 24 hours At lower temperatures and higher relative humidity the drying time is extended.				
Theoretically: 8-10 m ² with 1 l in 1 coat.				
The practical coverage depends on the wood treatment, type of surface and application methode.				
TESSAROL thinner				
	if necessary - max.5% max. 5% The paint, air and surfa Dust dry in approx. 3 hc At lower temperatures a Theoretically: 8-10 m²w The practical coverage	(DIN 4 mm) if necessary - max.5% max. 5% approx. 40 sec. delivery The paint, air and surface temperature should be Dust dry in approx. 3 hours, touch dry in 4 - 5 hou At lower temperatures and higher relative humidity Theoretically: 8-10 m² with 1 l in 1 coat. The practical coverage depends on the wood treat	(DIN 4 mm) if necessary - max.5% max. 5% approx. 40 sec. 1,2 – 1,5 mm delivery 0,23 – 0,28 mm The paint, air and surface temperature should be at least +5 °C. Dust dry in approx. 3 hours, touch dry in 4 - 5 hours, recoatable after 24 hours At lower temperatures and higher relative humidity the drying time is extended Theoretically: 8-10 m² with 1 l in 1 coat. The practical coverage depends on the wood treatment, type of surface and a	

SURFACE PREPARATION

Wooden surface

The humidity must not exceed 15% for coniferous trees, and 12% for deciduous trees. The dry surface is to be sanded and cleaned, and any wax, resin or grease should be removed with **NITRO thinner**.

Renovation of old coating

Undamaged coatings are to be cleaned and sanded, damaged coatings are to be removed completely.

COATING SYSTEMS

SURFACE		SURFACE PREPARATION	PRIMER	TOP COAT	
NEW WOOD	indoors	Sanding, removing impurities	BORI thin-layer wood stain – in the selected colour shade	2x TESSAROL varnish for boats	
	outdoors	=	in the selected colour shade	2 - 3x TESSAROL varnish for boats	
OLD COATINGS	indoors	cleaning, sanding and removing damaged coatings	in case of very damaged coats BORI thin-layer wood stain –	1 - 2x TESSAROL varnish for boats	
	outdoors	_	in the selected colour shade	2x TESSAROL varnish for boats	

This document updates and replaces all previous issues









NOTES AND SPECIAL FEATURES

- Colourless coatings do not provide sufficient protection against UV rays; therefore, we do not recommend using them as an independent coating for outdoor varnishing.
- For decorative effect, the wood may be pretreated with BORI thin-layer wood stain in the desired colour shade.
- For painting panels, we recommend the prior impregnation of the wood on both sides with **BORI thin-layer wood stain** or **BORI impregnation with biocide W** (outdoors, humid spaces), as this achieves an improved dimensional stability.
- A strong odor of organic solvents may appear in poorly ventilated spaces. We therefore do not recommend using paints on basis of solvent born alkyds for painting interior furniture parts.





III-2018